ZIBO JINGGAN REFRACTORY IMPORT AND EXPORT CO.,LTD

Address:NO. 3, Yanhe Road, Boshan, Zibo, Shandong, China Email:wp@cnjingganrefractory.com/sdwenping@163.com Contact:Rose Tel/Wechat:+86-13275332819 Tel:86-533-4188518 Fax:86-533-4188518

Castable for Hot Metal Slag Removal Ditch



1,Description of Castable for Hot Metal Slag Removal Ditch

Castable For Hot Metal Slag Removal Ditch is used in the slag removal ditch of the iron trough, carrying the flow of molten slag. The main raw materials used in the product are calcined dense bauxite, fused corundum sand and fused silicon carbide sand. The erosion resistance and slag corrosion resistance of the product are very good, and the use effect is very good.

2,Index of Castable for Hot Metal Slag Removal Ditch

Item		JTG-J3
Model		· · · · · · · · · · · · · · · · · · ·
Chemical composition %	Al2O3	≥65
	SiC+C	≥14
Bulk density g/cm ³	110℃*24h	≥2.65
	1000°C*3h	≥2.60
	1450°C*3h	≥2.60
Linear change rate %	1000°C*3h	≤0.5
	1450°C*3h	≤0.6
Bending strength MPa	110℃*24h	≥5.0

ZIBO JINGGAN REFRACTORY IMPORT AND EXPORT CO.,LTD

	1000°C*3h	≥6.0
	1450°C*3h	≥7.0
Crushing strength MPa	110℃*24h	30.0
	1000℃*3h	30.0
	1450°C*3h	40.0

3, Characteristics of Castable for Hot Metal Slag Removal Ditch

- 1)Castable for Hot Metal Slag Removal Ditch is mainly made of anhydrous tamping, black granular and easy to construct.
- 2)Storage of Castable for Hot Metal Slag Removal Ditch should be moisture-proof and waterproof.
- 4.Good feedback of product use effect, the products have been exported to Australia, Oman, Mexico
- 5.We are a professional supplier, who can provide customers with free product technology, use and other issues.

Do you want to find a professional supplier of refractory products?

Do you want to find a professional supplier of graphite electrodes?

Do you want to find a stable and credible supplier?

Then let's contact with jinggan company

Contact me: Email: wp@cnjingganrefractory.com/sdwenping@163.com

TEL: 86-0533-4188518 / FAX: 86-0533-4188518

Rose:+86-13275332819(wechat/whatsapp number)